



CALTEX

CalTex Plastics  
2380 East 51st Street  
Vernon, California 90058  
Tel : (323) 583-4140  
Fax : (323) 583-8402  
www.caltexplastics.com

## CALDRY 320

Jan. 2023

CALDRY 320 is a clear barrier material featuring an extremely low MVTR and OTR.

---

---

### PHYSICAL PROPERTIES (Proprietary Construction / Polyolefin)

TOTAL THICKNESS	4.5 mil
MOISTURE VAPOR TRANSMISSION RATE (ASTM F1249)	<0.005gr./100 in <sup>2</sup> 24 hrs.
O <sub>2</sub> TRANSMISSION RATE (MOCON)	.15cc/100 in <sup>2</sup> / 24 hrs.
TEAR STRENGTH (ASTM D1004-66 NOTCHED)	MD: 5.4 lb. TD: 6.2 lb.
TENSILE STRENGTH (ASTM D882-83, A)	MD: 12500 psi TD: 12500 psi
BURSTING STRENGTH (FTMS 191-C, 5122)	120 psi
PUNCTURE STRENGTH (FTMS 101-C, 2065.1)	> 21 psi
HEAT SEAL STRENGTH (ASTM D-1876-72)	> 12 lb./in.
LIGHT TRANSMISSION (ASTM D1003-77)	> 90%
WATER RESISTENCE (FTMS 101-C, 3028, F)	NO DELAMINATION

Caltex Plastics makes no warranty, expressed or implied, as to the suitability of these materials for any specific use. The values shown above were developed from random samples taken from production material. We believe them to be typical for the product. Actual values may vary somewhat from those depicted here. Customers should determine product suitability based upon their own internal criteria.