



CalTex Plastics
2380 East 51st Street
Vernon, California 90058
Tel : (323) 583-4140
Fax : (323) 583-8402
www.caltexplastics.com

CALVF 4D

Jan-23

CALVF 4D is ideal for packaging of critical components where protection against moisture and corrosion is necessary. It has a wide range of uses where a high barrier film is needed with a low WVTR. It is well suited for food packaging, where very low oxygen levels are required. It is specially designed to accommodate a variety of coffee applications.

PHYSICAL PROPERTIES (PET / adhesive / FOIL / adhesive / LLDPE)

TOTAL THICKNESS	4.5 mil
WATERVAPOR TRANSMISSION RATE (FED 101)	0.0006 gr./100 in ² 24 hrs.
O ₂ TRANSMISSION RATE (MOCON)	0.001/cc/m ² /24 hrs.
TENSILE STRENGTH (INSTRON TAPPI T404)	25 psi
BURSTING STRENGTH (MULLEN TAPPI T403)	69 psi
PUNCTURE STRENGTH (FTMS 101-C, 2065.1)	> 16 psi
BREAKING STRENGTH (GRAB FED 191)	70 lb.

Caltex Plastics makes no warranty, expressed or implied, as to the suitability of these materials for any specific use. The values shown above were developed from random samples taken from production material. We believe them to be typical for the product. Actual values may vary somewhat from those depicted here. Customers should determine product suitability based upon their own internal criteria.